

AO Wax (Rubber Protective Wax)

SPECIFICATIONS

PROPERTIES	NOMINAL VALUE	TEST METHOD
Drop Melting Point / °C	62 - 67	GB/T 8026-2014
Penetration @ 25 °C / (1/10mm)	9 Min	GB/T 4985
Non-Normal Alkane Content / % (Mass Fraction)	40 Min	SH/T 0653-2021
Kinematic Viscosity @ 100 °C / (mm²/s)	5.0 - 8.5	GB/T 265-1988 (2004)
Color/NO.	2.0 Max	GB/T 6540-1986 (2004)
Oil Content / % (Mass Fraction)	2.0 Max	GB/T 3554-2008
Ash Content / % (Mass Fraction)	0.03 Max	GB/T 508-1985 (2004)
Thermal Weight Loss / % (Mass Fraction)	0.2 Max	NB/SH/T 0871-2021 APPENDIX A
Mechanical Impurity and Moisture	NONE	Visualization

