



Technical Data Sheet

QUREACC®DPG

Product Code	30004
Composition	Diphenyl Guanidine
CAS No.	102-06-7
EC No.	203-002-1
Molecular Formula	C ₁₃ H ₁₃ N ₃
Molecular Weight	211

Property	Unit	Typical Value	Test Method
Appearance	-	White to Light Pinkish Powder Low Dust	Visual
Assay	%	98.0 min.	ASTM D 5054
Melting point	°C	143 - 150	QCD/TM/25
Specific gravity @ 25°C	-	1.17 - 1.21	QCD/TM/132
Loss on drying (70°C, 2 hrs)	%	0.5 max.	QCD/TM/24
Ash content	%	0.5 max.	QCD/TM/11

Application:

QUREACC®DPG gives very long scorch time and relatively slow full cure. It cause slight discoloration and cannot be used in light coloured articles, except as an activator. When it is used on its own, the resistance of the vulcanization to hot air and oxygen is poor. Accelerators of the mercapto types are strongly activated by this product. It is used in moulding large NR based technical goods where slow cure is required.

Packing:

Available in 25 Kgs paper bags.

Storage stability:

Store in a cool and dry place. Stable for up to 24 months from the date of manufacturing when stored in the original packing material in a cool and dry environment.

Safety:

Please refer safety data sheet.

Rev.3.1 DT. 19.05.2022

QUREACC is a registered trademark of YASHO INDUSTRIES LIMITED and/or its respective wholly owned subsidiaries

YASHO INDUSTRIES LIMITED

REGISTERED OFFICE: Office No. 101/102, Peninsula Heights, C.D.Barfiwala Marg, Juhu lane, Andheri (West), Mumbai - 400058, India
TEL : +91 22 62510100/FAX : +91 22 62510199 E-Mail: info@yashoindustries.com

FACTORY - UNIT II: Plot No. 1713, Phase III, G.I.D.C., Vapi - 396 195, Gujarat, India TEL.: +91 260 2420896 / 2423896

Although every care has been taken in the completion of the above information & recommendation they are offered in good faith without guarantee.

www.yashoindustries.com



+91 9323008200
022-23612222
022-23632222



exports@skyimpex.biz



skyimpexindia.com



Register Office: 12 Panorama Building,
203 Walkeshwar Road, Mumbai-400006